

GUANGDONG WONDER TESTING INTERNATIONAL CO., LTD.

TEST REPORT

Report No.: WDX19071004EN
Applicant: GUANGZHOU YAKEDA OUTDOORS TRAVEL
PRODUCTS CO., LTD
Address: YANGER VILLAGE, SHLING TOWN, HUADU
DISTRICT, GUANGZHOU CHINA
Date: Jul. 29, 2019

Edited by: *Starr Lu.* Reviewed by: *Nancy Liang* Approved by: *Shua Wang*

The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full or in part, without prior written permission of the company. The data/results in reports without an CMA stamp do not have a proven effect. Items marked with "n" means they are not tested. "s" means the item of subcontractor is not accredited by CNAS.

WONDER (GUANGDONG) TESTING INTERNATIONAL CO., LTD. No. 221 Jianshebei Road Huadu District, Guangzhou City, Guangdong Province, China, E-mail: wd@wdwonder.com Tel: 86-020-8689 0001 Fax: 86-020-8689 6998 Website: http://www.wonder.com



Report No.: WDX19071004EN

Date: Jul. 29, 2019

Page: 1 / 3

Applicant: GUANGZHOU YAKEDA OUTDOORS TRAVEL PRODUCSTS CO., LTD

Address: YANGER VILLAGE,SHLING TOWN,HUADU DISTRICT,GUANGZHOU CHINA

The following merchandise was (were) submitted and identified by client as:

Sample Name: 600D/6*6*74T

Number of Sample: 1pc

Sample Received Date: Jul. 26, 2019

Completed Date: Jul. 29, 2019

Test Result(s): Please refer to next page(s).

Test Requested and Conclusion(s):

No.	Test Sample	Standard and Requirement	Conclusion(s)
1	Submitted samples	Water repellency: Spray Test	DATA
2	Submitted samples	Fabric weight	DATA
3	Submitted samples	Tear strength test	DATA



Report No.: WDX19071004EN

Date: Jul. 29, 2019

Page: 2 / 3

Test Result(s):

Water repellency: Spray Test

Method: With reference to AATCC 22-2010.

Material No.	Specimen No.	Results
1	#1	90
	#2	90
	#3	90
	average	90

Note: Standard spray test ratings

- 100 (ISO 5) No Sticking Or Wetting Of The Specimen Face
- 90 (ISO 4) Slight Random Sticking Or Wetting Of The Specimen Face
- 80 (ISO 3) Wetting Of The Specimen Face At Spray Points
- 70 (ISO 2) Partial Wetting Of The Specimen Face Beyond The Spray Points
- 50 (ISO 1) Complete Wetting Of The Specimen Face Beyond The Spray Points
- 0 Complete Wetting Of The Entire Face Of The Specimen

Fabric Weight

Method: ASTM D 3776-09a(2013), Method C, Sampling area:100cm².

Material No.	Results
1	450.9 g/m ² 13.3 oz/yd ²

Tear strength: impact pendulum method

Method:ASTM D5587-2015.

Material No.	Test item	Result (lbf)
1	Warp	71.2
	Weft	39.6

Test Material List

Material No.	Description	Location
1	Black woven fabric	Body

The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full, without prior written permission of the company. The data/results in reports without an CMA stamp do not have a proven effect. Items marked with "n" means they are not accredited by CNAS, "s" means the item of subcontractor is not accredited by CNAS.



Report No.: WDX19071004EN

Date: Jul. 29, 2019

Page: 3 / 3

Photo(s) of Sample(s):



End of Report

The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full, without prior written permission of the company. The data/results in reports without a CMA stamp do not have a proven effect. Items marked with "n" means they are not accredited by CNAS, "s" means the item of subcontractor is not accredited by CNAS.

WONDER (GUANGDONG) TESTING INTERNATIONAL CO., LTD. No. 221 Jianshebei Road Huadu District, Guangzhou City, Guangdong Province, China, 510800

E-mail: wd@wdwonder.com Tel: 86-020-8689 0001 Fax: 86-020-8689 6998 Website: <http://www.wdwonder.com>